ポリオキソメタレートとクロム錯体から成る多孔性イオン結晶を 用いた水素発生反応

(東大院総合文化 ¹) ○浅田 響 ¹・堤 由太朗 ¹・下山 雄人 ¹・内田 さやか ¹ Hydrogen evolution reaction using porous ionic crystals with polyoxometalates and chromium complexes (¹*Graduate School of Arts and Sciences, The University of Tokyo*)○Hibiki Asada,¹ Yutaro Tsutsumi,¹ Yuto Shimoyama,¹ Sayaka Uchida¹

Toward the realization of a sustainable energy society, polyoxometalates (POMs) with multielectron redox properties are expected to catalyze hydrogen evolution reactions (HER). Although previous studies on POM-immobilized composites have reported high electrocatalytic activity, the role of POM has remained unclear. In this study, three types of porous ionic crystals (PICs) composed of Keggin-type POMs ([Co^{II}W^{VI}₁₂O₄₀]⁶⁻, [Zn^{II}W^{VI}₁₂O₄₀]⁶⁻, [Co^{II}W^{VI}₁₁V^{IV}O₄₀]⁸⁻) and a chromium complex [Cr₃O(OOCCH₂CN)₆(H₂O)₃]⁺ are used as electrocatalysts for HER. The η10 values, representing the overpotential to achieve a current density of 10 mA cm⁻², was evaluated by linear sweep voltammetry (LSV), and the PIC with [CoW₁₁VO₄₀]⁸⁻ showed the smallest η10 value and superior performance. At the meeting, the HER mechanism will be discussed on the basis of the crystal structure of PICs and the electronic structure using the XANES region of X-ray absorption spectroscopy. Keywords: Polyoxometalate: Water-splitting: Porous materials: Ionic crystal: Hydrogen

Keywords: Polyoxometalate; Water-splitting; Porous materials; Ionic crystal; Hydrogen evolution reaction

持続可能なエネルギー社会の実現に向け、多電子酸 化還元能を有するポリオキソメタレート(POM)は水素 発生反応(HER)触媒として期待されている。これまで に、POM を固定化した複合材料が HER 電極触媒とし て高活性を示すことが報告されているが、POM の役割 が不明瞭であった¹。本研究では、Keggin型 POM([Co $^{II}W^{VI}_{12}O_{40}]^{6-}$, $[Zn^{II}W^{VI}_{12}O_{40}]^{6-}$, $[Co^{II}W^{VI}_{11}V^{IV}O_{40}]^{8-}) \geq \mathcal{I}$ ロム錯体 [Cr₃O(OOCCH₂CN)₆(H₂O)₃]⁺を構成ユニット とする3種の多孔性イオン結晶 (PICs) を HER 電極触 媒として利用した(Fig.1)。電位掃引に対する電流 応答(LSV 測定)により過電圧 η10 (10mA/cm²を与 える電圧)を評価した結果、[CoW₁₁VO₄₀]⁸⁻を含む P IC 触媒が最も小さな値を示し、触媒として優れる ことがわかった(Fig.2)。発表当日は、反応メカニ ズムについて、PICs の結晶構造やX線吸収分光の XANES 領域を用いた電子状態を基に議論する予 定である。

1) D. M. Fernandes et al., ChemElectroChem, 2018, 5, 273




Fig.1. PICs の結晶構造 (灰色:[WO6],[VW5O6] ユニット 茶色:[CrO5N] ユニット)




Fig.2. PICs Ø η10