

口頭発表 | セッション記号 U (ユニオン) | ユニオン

[U-05_30PM2] 生命-水-鉱物-大気相互作用

コンビーナ:*大竹 翼(北海道大学大学院工学研究院 環境循環システム部門)、鈴木 庸平(東京大学大学院理学系研究科)、白石 史人(広島大学大学院理学研究科地球惑星システム学専攻)、高井 研(海洋研究開発機構極限環境生物圏研究センター)、上野 雄一郎(東京工業大学大学院地球惑星科学専攻)、長沼 毅(広島大学大学院生物圏科学研究科)、掛川 武(東北大学大学院理学研究科地学専攻)、横山 正(大阪大学大学院理学研究科宇宙地球科学専攻)、中村 謙太郎(独立行政法人海洋研究開発機構 (JAMSTEC) システム地球ラボ プレカンブリアンエコシステムラボユニット)、座長:鈴木 庸平(東京大学大学院理学系研究科)、長沼 毅(広島大学大学院生物圏科学研究科)

2014年4月30日(水) 16:15 ~ 17:45 419 (4F)

地球における生命活動は、地球における様々な物理・化学的なダイナミズム及びプロセスと密接に関わっている。その本質とは、生命活動、水、鉱物（固体地球）、大気の各因子間あるいは多能的に生じる相互作用である。この生命-水-鉱物-大気相互作用を単一の科学領域で解き明かすことは不可能であり、多様な研究分野、研究者或いは研究アイデア及び手法の連携が不可欠である。本セッションはその道標となる場を提供する。

17:15 ~ 17:30

[U05-P14_PG]A novel remediation method for nickel-bearing wastewater at neutral conditions

ポスター講演3分口頭発表枠

*岡橋 東子¹、西内 亨¹、佐藤 努²、大竹 翼²、米田 哲朗² (1.北大・工学院、2.北大・工学研究院)

キーワード: Remediation, Layered double hydroxide, Nickel

Advances in technology such as the electronics and metal plating industries have increased the demand of Ni year by year. On the other hand, the resources are unevenly distributed in a few countries and the supply is highly dependent on strategic policies. Moreover, since Ni is not produced in Japan and it is dependent on imports from foreign countries, the supply structures of Ni are vulnerable. Because of this, the necessity of recovering Ni from wastewaters and other waste forms has been increasing. Some industrial wastewaters contain large amounts of Ni. Generally, the removal of Ni from contaminated wastewater by adding antalkaline and flocculants to increase the pH to 10 or above would result in the generation of Ni-hydroxides after treatment. After that, it is necessary to adjust the pH below the effluent standard (pH 5.8~8.6). However, this method suffers from some disadvantages, such as the high cost for chemical reagents, problems in the disposal of alkali sludge and inefficient treatment system. Therefore, a more sustainable remediation method must be developed to achieve sustainable wastewater treatment operations. This study focused on natural attenuation processes which are safer, cost-effective and more environmentally friendly than traditional methods. For example, at Dougamaru abandoned mine in Japan, high concentrations of Cu and Zn in wastewater are naturally incorporated in the structure of layered double hydroxides (LDH), which forms in the presence of Al ions, hence, natural attenuation of Cu and Zn occurs (Okamoto et al., 2010). Because LDH has the hydroxide structure, six-coordinated heavy metals such as Cu, Ni and Co can be incorporated into the structure during the formation process. Therefore the objective of this study is to develop a remediation method for Ni-bearing wastewaters at neutral conditions, and to clarify the behavior of Ni in the neutralization and precipitation process.

In this context, to check the applicability of LDH in the treatment of Ni-bearing wastewaters, synthesis experiments were carried out by co-precipitation of Ni-bearing LDHs containing SO_4^{2-} as the interlayer anion with different concentrations of dissolved Al ions. Analysis of water chemistry before and after the co-precipitation show that the removal efficiencies of Ni from the synthetic wastewaters increased

with increasing dissolved Al concentration. The results further show that the presence of Al in the formation of LDH removed Ni at pH values lower than previous methods which precipitated Ni-hydroxides. It is expected that treatment costs will be reduced in actual wastewater treatment systems because Al addition leads to the reduction of antalkaline use and the neutralization process. Ni adsorption experiments and extraction experiments were conducted to investigate the sorption behavior of Ni. Only a small amount of Ni was adsorbed to LDH and basaluminite (major minerals in coprecipitation experiments) as inner- and outer-sphere complexes. From the result of XAFS analysis, Ni was incorporated into the structure by being able to precipitate LDH selectively. This shows Ni is fixed securely in the structure of LDH and that the mobility of Ni will be governed by the solubility of LDH. Thermodynamic modeling suggests that the precipitation of LDHs with the optimum Al/Ni molar ratio (0.25~0.50) is determined by the initial conditions (e.g. pH, Al, Ni concentrations). Furthermore, modeling results reproduce the experimental results such as removal efficiency and mineral species well, opening the possibility of its application in actual wastewater treatment operations.